

Employment of PLASTRONFOAM products

Application:	Multi-layer film for food packaging
Process:	Chemical foaming
Raw materials:	50µm PE; 15µm ADH; 20µm EVOH; 15µm ADH; 500µm EPP
Extrusion line:	EUROTECNO, air-cooled
Density:	0,77 g/cm ³
Blowing agent:	PLASTRONFOAM C 50
Dosage of BA:	0,7 %

