

Employment of PLASTRONFOAM products

Application:	Lever for seat adjustment of a passenger car
Process:	Injection moulding
Raw material:	PP
Modification of mould:	none
Cavities:	4
Melt temperature:	250 °C
Blowing agent	PLASTRONFOAM C 7,5
Dosage of BA:	0, 8 %
Target:	Sink mark reduction



Before



Afterwards



Cross section